Selkie Panel Adhesive

Revision: 16/02/2021 Page 1 from 1

Technical data

| Basis | SBR rubber |
|-------------------------|--|
| Consistancy | Paste |
| Curing system | Physical drying |
| Curing speed * | Hand tight in 20 min. |
| Temperature resistance | -20 °C → 60 °C |
| Open time (*) | Ca. 15 min. |
| Application temperature | $5 ^{\circ}\text{C} \rightarrow 30 ^{\circ}\text{C}$ |

^(*) these values may vary depending on environmental factors such as temperature, moisture, and type of substrates.

Product description

Selkie Panel Adhesive is a ready to use, solvented construction adhesive based on synthetic rubber.

Properties

- Universal use
- Makes the use of screws and nails redundant.
- Water resistant
- Suitable for bonding polystyrene

Applications

- All bonding in assembly techniques.
- Bonding in the renovation industry.
- Bonding in construction industry.
- Bonding of cable trays and panels.

Packaging

Colour: beige

Packaging: 310ml koker

Shelf life

12 months in unopened packaging in a cool and dry storage place at temperatures between +5°C and +25°C.

Substrates

Nature: clean, free of dust and grease. Surface preparation: No pretreatment required Selkie Panel Adhesive has excellent adhesion on most substrates. There is no adhesion on PE, PP, PTFE (Teflon®) and bituminous substrates. We recommend a preliminary compatibility test.

Application method

Apply the adhesive in equal beads or dots on one of the materials that need to be glued. Always apply adhesive to the edges and corners. Press both parts together, immediately pull loose and let dry for 10-15 minutes. Afterwards bond again and batten with a rubber hammer. Support if necessary. Cleaning: white spirit acetone

Repair: With the same material

Health- and Safety Recommendations

Take the usual labour hygiene into account. Consult label and material safety data sheet for more information.

Remark: This technical data sheet replaces al previous versions. The directives contained in this documentation are the result of our experiments and of our experience and have been submitted in good faith. Because of the diversity of the materials and substrates and the great number of possible applications which are out of our control, we cannot accept any responsibility for the results obtained. Since the design, the quality of the substrate and processing conditions beyond our control, no liability under this publication are accepted. In every case it is recommended to carry out preliminary experiments. Soudal reserves the right to modify products without prior notice.